



VERTEC 1009

Compression Molded

VERTEC 1009™ is a polymer filled PTFE (polytetrafluoroethylene) material. It exhibits good sealability, creep resistance, very low coefficient of friction and low wear rate under dry running conditions. Its non-abrasive nature makes it an ideal sealing material for use against soft metal surfaces in dynamic applications. It will service steam use, making it a good candidate where VERTEC 1011 is not acceptable.

<i>Physical Properties</i>	<i>ASTM Method</i>	<i>Typical Values</i>
Specific Gravity	D792	2.0 gr/cm ³
Water Absorption (24hrs. @73.4°F)	D570	.01 %
Color	N/A	Light Brown

<i>Mechanical Properties</i>		
Tensile Strength	D1708	2000 psi
Tensile Elongation	D1708	160 %
Flexural Strength	D790	2300 psi
Flexural Modulus	D790	150,000 psi
Compressive Strength	D695	1300 psi
Compressive Modulus	D695	psi
Impact Strength (Izod, notched)	D256	ft-lb/in
Hardness	Shore D	65

<i>Tribological Properties</i>		
Coefficient of Friction		
Static	D3702	.13
Dynamic	D3702	.08
Wear Rate (PV: 20,000 psi-fpm)	D3702	µin/min

<i>Thermal Properties</i>		
Coefficient of Linear Thermal Expansion (78 to 400°F)	D696	57 10 ⁻⁶ /°F
Heat Deflection Temperature (@264 psi)	D648	°F
Glass Transition Temperature (T _g)	D3418	266
Continuous Service Temperature (Max @ no load)		450 °F
Melting Point		648 °F

<i>Electrical Properties</i>		
Volume Resistivity	D257	10 ¹⁶ ohm-cm
Dielectric Strength	D149	KV/mm
Dielectric Constant	D150	50Hz, 200°C

Note: Property values should be interpreted as typical rather than minimum value. All technical information and recommendations are presented in good faith, based upon laboratory and real-world tests believed to be reliable and practical. However, Vertec Polymers cannot guarantee the accuracy or completeness of this information, and it is the customer's responsibility to determine product suitability to any given application.

Rev. Date 05/2004